

SiSiB® AF8250-120 Dual-end Amino Silicone Fluid

INTRODUCTION

SiSiB® AF8250-120 is 3-Aminopropyl Terminated Polydimethylsiloxane. SiSiB® AF8250-120 can be used as a raw material or additive for the preparation of copolymers through polyaddition or polycondensation reactions.

CHEMICAL STRUCTURE

$$H_2N$$
— $(CH_2)_3$ — Si — O — Si — O — Si — O — Si — CH_3
 CH_3
 CH_3
 CH_3
 CH_3
 CH_3
 CH_3
 CH_3
 CH_3
 CH_3

CAS NUMBER

97917-34-5 / 106214-84-0

EINECS NUMBER

N.A.

PHYSICAL PROPERTIES

Appearance	Colorless Clear Liquid
Viscosity (25°C)	120 cSt
Density (25°C)	0.96
Refractive Index (25°C)	1.406
Typical Amine Content	0.4 meq/g

APPLICATIONS

SiSiB® AF8250-120 amino silicone fluid series offers the well-known processing properties of standard silicones. Due to their symmetric substitution, the downstream products and copolymers exhibit the typical characteristics of linear materials.

SiSiB® AF8250-120 can be used as raw materials for chemical synthesis, polymer modification and additivation, and copolymerization with organic monomers.

Additionally, SiSiB® AF8250-120 can be used as reactive silicone additives for polyurethanes, polyamides, polyimides, and polyureas.

PACKING

 $\mbox{SiSiB}\mbox{\ensuremath{\mathbb{R}}}$ AF8250-120 is available in 25Kg pails or 200Kg steel drum.



SiSiB® AF8250-120 Dual-end Amino Silicone Fluid

HANDLING This document does not contain the product safety information required for

safe use. Before handling, please refer to the product and safety data sheets, as well as container labels, for information on safe usage, physical hazards, and health risks. Safety Data Sheet is available on the website,

from the distributor, or by contacting SiSiB customer service.

STORAGE In the original unopened packaging, SiSiB® AF8250-120 has a shelf life of

24 months in a dry and cool place.

NOTE All information in the leaflet is based on our present knowledge and

experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product

described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for

a particular purpose or merchantability.

We disclaim liability for any incidental or consequential damages.