


SiSiB® AF8250-35 Dual-end Amino Silicone Fluid

INTRODUCTION

SiSiB® AF8250-35 is 3-Aminopropyl Terminated Polydimethylsiloxane. SiSiB® AF8250-35 can be used as a raw material or additive for the preparation of copolymers through polyaddition or polycondensation reactions.

CHEMICAL STRUCTURE



CAS NUMBER

97917-34-5 / 106214-84-0

EINECS NUMBER

N.A.

PHYSICAL PROPERTIES

Appearance	Colorless Clear Liquid
Viscosity (25°C)	35 cSt
Density (25°C)	0.96
Refractive Index (25°C)	1.412
Typical Amine Content	1.0 meq/g

APPLICATIONS

SiSiB® AF8250-35 amino silicone fluid series offers the well-known processing properties of standard silicones. Due to their symmetric substitution, the downstream products and copolymers exhibit the typical characteristics of linear materials.

SiSiB® AF8250-35 can be used as raw materials for chemical synthesis, polymer modification and additivation, and copolymerization with organic monomers.

Additionally, SiSiB® AF8250-35 can be used as reactive silicone additives for polyurethanes, polyamides, polyimides, and polyureas.

PACKING

SiSiB® AF8250-35 is available in 25Kg pails or 200Kg steel drum.

SiSiB® AF8250-35 Dual-end Amino Silicone Fluid

HANDLING

This document does not contain the product safety information required for safe use. Before handling, please refer to the product and safety data sheets, as well as container labels, for information on safe usage, physical hazards, and health risks. Safety Data Sheet is available on the website, from the distributor, or by contacting SiSiB customer service.

STORAGE

In the original unopened packaging, SiSiB® AF8250-35 has a shelf life of 24 months in a dry and cool place.

NOTE

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability.

We disclaim liability for any incidental or consequential damages.