
SiSiB® HF2079 Phenylsilsesquioxanes Hydrogen-terminated

CHEMICAL NAME

Hydride Terminated Polyphenyl-(dimethylsiloxy)siloxane

CHEMICAL STRUCTURE



INTRODUCTION

SiSiB® HF2079 is a T-type polyphenylsiloxane, terminated by hydride, miscibility with dimethyl siloxane, liquid silicone rubber, phenyl silicone rubber and phenyl resin.

TYPICAL PHYSICAL PROPERTIES

CAS No.	68952-30-7
Color and Appearance	Colorless clear liquid
Active Ingredient	100%
Refractive Index 25°C	1.510~1.540
Hydrogen Content	0.25~0.29%
Viscosity 25°C	4000~6000 cSt
Volatile, %	Max. 2.0
Acid Value (ppm)	Max. 5.0

APPLICATIONS

SINOPCC GROUP

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil: Trademark of SINOPCC Group Limited or its affiliated. © 2018 SINOPCC Group Limited. All rights reserved. For further information, please see www.SiSiB.com.

SiSiB[®] HF2079

Phenylsilsesquioxanes Hydrogen-terminated

SiSiB® HF2079 is used as crosslinker for liquid silicone rubber, phenyl silicone rubber and phenyl resin.

PACKING AND STORAGE

SiSiB® HF2079 is supplied in 5Kg, 25Kg pail or 200Kg steel drum.

In the original unopened packaging, SiSiB® HF2079 has a shelf life of one year in a dry and cool place.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.

SINOPCC GROUP

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil: Trademark of SINOPCC Group Limited or its affiliated. © 2018 SINOPCC Group Limited. All rights reserved. For further information, please see www.SiSiB.com.