


SiSiB[®] PF1070-1000

OH Polymer 1000cSt

CHEMICAL NAME

α,ω -silanol-terminated polydimethylsiloxane (α,ω -Dihydroxypolydimethylsiloxane)

CHEMICAL STRUCTURE



INTRODUCTION

SiSiB[®] PC1070-1000 OH polymer is silanol terminated polydimethylsiloxane of 1000cSt viscosity; it is used as base polymer for the production of RTV silicone sealants.

TYPICAL PHYSICAL PROPERTIES

| | |
|----------------------------------|------------------------------|
| CAS No. | 70131-67-8 |
| Color and Appearance | Colorless transparent liquid |
| Density _{25/25°C} | 0.96-0.98 |
| Refractive Index _{25°C} | 1.401-1.403 |
| Viscosity | 1000cSt |

APPLICATIONS

Condensation cure one-part and two-part RTV systems are formulated from silanol terminated polymers with molecular weights ranging from 15,000 to 150,000. One-part systems are the most widely used. One-part systems are crosslinked with moisture-sensitive multi-functional silanes in a two stage reaction. In the first stage, after compounding with fillers, the silanol is reacted with an excess of multi-functional silane. The silanol is in essence displaced by the silane.

The reactivity of silanol fluids is utilized in applications other than RTV's. Low viscosity silanol fluids are employed as filler treatments and structure control additives in silicone rubber compounding. Intermediate viscosity, 1000-10,000 cSt. fluids can be applied to

SiSiB® PF1070-1000

OH Polymer 1000cSt

textiles as durable fabric softeners. High viscosity silanol terminated fluids form the matrix component in tackifiers and pressure sensitive adhesives.

PACKING AND STORAGE

SiSiB® PF1070-1000 OH polymer is supplied in 190Kg steel drum or 950Kg IBC container.

In the original unopened packaging, SiSiB® PF1070-1000 polymer has a shelf life of 18 months in a dry and cool place.

NOTES

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.