# SiSiB<sup>®</sup> STP51303

### Silane Terminated Polyether Polymer

### INTRODUCTION

SiSiB® STP51303 is alkoxy silane terminated polyether polymer. It could be used in moisture curing elastic sealant, elastic structure sealant and sealing coatings to achieve excellent adhesion to various substrates.

SiSiB® STP51303 based system is free of solvent, isocyanate, bubbles and odor during curing, which is quite different from polyurethane and silicone system. It is especially suitable for construction industry, transportation industry and general industry application.

#### PHYSICAL PROPERTIES

Component:	Silane Terminated Polyether Polymer
Appearance:	Yellow Liquid
Boiling point:	>250°C
Density 25°C:	1.00g/cm <sup>3</sup>
Viscosity 25°C:	10000~15000cP
Flash point:	> 237°C
Water solubility/miscibility	Virtually insoluble

### **FEATURES**

Moderate Activity, Moderate Modulus
Good adhesion strength
Fast curing , non-tin catalysts used if needed
Excellent anti-aging, anti-yellowing property
Excellent water resistance, chemical corrosion resistance
Excellent elastic recovery rate
Excellent storage stability
Solvent free, odorless, eco-friendly
Could be blended with other STP polymers

### APPLICATION

SiSiB® STP51303 polymer can be used as base polymer in elastic sealants, elastic structure sealants, encapsulate adhesives and coatings. The curing mode of the polymer is moisture curing; it can be made into a single component or two-component system.

**SINOPCC GROUP** 

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil: Trademark of SINOPCC Group Limited or its affiliated. © 2018 SINOPCC Group Limited. All rights reserved. For further information, please see www.SiSiB.com.

## SiSiB<sup>®</sup> STP51303

## Silane Terminated Polyether Polymer

Low modulus construction sealant
Transportation industry elastic sealant
Personal DIY sealant
Eco-friendly decoration sealant

### PROCESSING

SiSiB® STP51303 polymer dissolves readily in standard organic solvents. It is virtually insoluble in water. Despite its highly reactive terminal groups, uncatalyzed STP51303 is stable in air for several days. However, its reactivity with water or atmospheric humidity must be taken into account during storage and processing, since the material will slowly starts to condensate.

SiSiB® STP51303 polymer can be formulated by conventional methods and mixing processes. Water scavengers should be added to stabilize the formulations against premature curing during compounding or as a result of exposure to moisture during storage, particularly for vinyltrimethoxysilane.

### PACKING AND STORAGE

SiSiB® STP51303 is supplied in 200Kg steel drum or 1000Kg IBC tote.

In the unopened original container SiSiB® STP51303 has a shelf life of one year in a dry and cool place.

### Notes

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability. We disclaim liability for any incidental or consequential damages.

### July 2024 | Technical Data Sheet | Edition SR

Please send all technical questions concerning quality and product safety to: support@SiSiB.com.

SINOPCC GROUP

AddSil, CoatSil, Kolark, PowSil, SinoSil, SiSiB, WinSil: Trademark of SINOPCC Group Limited or its affiliated. © 2018 SINOPCC Group Limited. All rights reserved. For further information, please see www.SiSiB.com.