

ADDSiL™ 8310 Silicone Leveling Agent

INTRODUCTION

ADDSiL™ 8310 is solution of a polyether modified polydimethylsiloxane.

Effects

Transparency in clear formulation:	★★★★★
Defoaming effect:	★★
Dynamic surface tension:	★★★
Static surface tension:	★★★
Slip effect:	★★★★★
Reduce orange peel effect:	★★

PHYSICAL PROPERTIES

Color and Appearance	Slight yellowish clear liquid
Solvent	Xylene
Active Ingredient	25%
Density 25°C	0.88~0.92g/ml
Viscosity 25°C	5~25s (T-4 viscometer)
Recommended Levels	0.1~0.5%

BENEFITS

- Reduced surface tension of coating systems.
- Improved substrate wetting.
- Avoids cratering.
- Increased surface slip and gloss.
- Thermostable, can be used for baking system.
- Good recoating and no loss in in adhesion.

APPLICATIONS

- Solvent based
- UV Curing

ADDSiL™ 8310 is silicone-based surface additive for solvent-borne and UV curing system. It can provide strong reduction of the surface tension of coating systems. It therefore particularly improves substrate wetting and avoids cratering. Surface slip and gloss are also increased.

ADDSiL™ 8310 is a thermostable silicone additive which, in contrast to conventional silicones, shows no thermal decomposition at high temperature.

ADDSiL™ 8310 Silicone Leveling Agent

RECOMMENDED DOSAGE

The recommended dosage is 0.1~0.5% of the total formulations.

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

The additive can be incorporated during any stage of the production process, including post-addition.

PACKING

ADDSiL™ 8310 is supplied in 20Kg / 180Kg plastic drum or steel drum or according to customer's request.

Separation or turbidity may occur at temperatures below 5°C. Warm to 20°C and mix well.

HANDLING

This document does not contain the product safety information required for safe use. Before handling, please refer to the product and safety data sheets, as well as container labels, for information on safe usage, physical hazards, and health risks. Safety Data Sheet is available on the website, from the distributor, or by contacting SiSiB customer service.

STORAGE

In the original unopened packaging, ADDSiL™ 8310 has a shelf life of 24 months.

NOTE

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability.

We disclaim liability for any incidental or consequential damages.