

ADDSiL™ 8570 Silicone Leveling Agent

INTRODUCTION

ADDSiL™ 8570 is polyether modified polydimethyl siloxane.

ADDSiL™ 8570 can provide slip, gloss enhancement, pigment treatment and leveling for ink and coating applications.

ADDSiL™ 8570 can provide mar resistance for coating applications.

ADDSiL™ 8570 compatible with acrylic, alkyd, amide, epoxy, nitrocellulose, phenolic, polyester, polyurethane and vinyl systems.

Effects

Transparency in clear formulation:	★★★★★
Defoaming effect:	★
Dynamic surface tension:	★★★★★
Static surface tension:	★★★★★
Slip effect:	★★★★★
Reduce orange peel effect:	★

PHYSICAL PROPERTIES

Color and Appearance	Transparent to slight yellowish clear liquid
Active Ingredient	100%
Flash Point	>100°C
Recommended Levels	0.05~0.5%

APPLICATIONS

ADDSiL™ 8570 can provide slip, gloss enhancement, pigment treatment and leveling for ink and coatings applications.

ADDSiL™ 8570 can provide good recoating and minimal influence on adhesion of coating films.

ADDSiL™ 8570 can provide mar resistance for coatings applications.

RECOMMENDED DOSAGE

The recommended dosage is 0.05~0.5% of the total formulations, 0.05~0.5% in UV system.

The above recommended levels can be used for orientation. Optimal levels

ADDSiL™ 8570 Silicone Leveling Agent

are determined through a series of laboratory tests.

It is added during any stage of the production process including post-addition.

PACKING

Separation or turbidity may occur at temperatures below 5 °C. Warm to 20 °C and mix well.

ADDSiL™ 8570 is supplied in 25Kg / 200Kg plastic drum or steel drum or according to customer's request.

HANDLING

This document does not contain the product safety information required for safe use. Before handling, please refer to the product and safety data sheets, as well as container labels, for information on safe usage, physical hazards, and health risks. Safety Data Sheet is available on the website, from the distributor, or by contacting SiSiB customer service.

STORAGE

In the original unopened packaging, ADDSiL™ 8570 has a shelf life of 24 months.

Separation or turbidity may occur at temperatures below 5°C. Warm to 20°C and mix well.

NOTE

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability.

We disclaim liability for any incidental or consequential damages.