

KOBOND™ 9004 Rheology Additive

INTRODUCTION

KOBOND™ 9004 is a dispersion of polyamide wax rheology modifier with good dispersion and good rheology.

KOBOND™ 9004 is widely used as anti-sagging and anti-settling agent and is suitable for various of solvent-based systems.

BENEFITS / EFFECTS

- KOBOND™ 9004 can be used in wood varnish for anti-settling.
- KOBOND™ 9004 is suitable for solvent varnish system. It can increase the viscosity quickly and make the coating with good anti-settling and anti-sagging properties.

PHYSICAL PROPERTIES

Color and Appearance	Yellowish to white liquid
Ingredient	Dispersion of polyamide wax
Active content	20%
Solvent	BTX aromatics

APPLICATIONS

- KOBOND™ 9004 is used in all solvent-based coating systems.

RECOMMENDED DOSAGE

Recommended dosage:

0.5% ~ 2.0% of the total formulation for anti-settling.

2.0% ~ 5.0% of the total formulation for anti-sagging.

Post-addition is possible, the above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

PACKING

KOBOND™ 9004 is supplied in 25Kg pail.

HANDLING

This document does not contain the product safety information required for safe use. Before handling, please refer to the product and safety data sheets, as well as container labels, for information on safe usage, physical hazards, and health risks. Safety Data Sheet is available on the website, from the distributor, or by contacting SiSiB customer service.

STORAGE

When stored at temperatures between 10°C and 35°C in the original unopened containers, KOBOND™ 9004 has a shelf life of 24 months from the date of production.

KOBOND™ 9004 Rheology Additive

NOTE

All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.

We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability.

We disclaim liability for any incidental or consequential damages.