SINOPCC GROUP

KOBOND™ 8130 Dispersant

INTRODUCTIONKOBOND™ 8130 is a copolymeric dispersant which is suitable for organic
pigments especially in solvent-borne coating systems.

BENEFITS / EFFECTS KOBOND[™] 8130 is suitable for all kinds of pigment dispersion, especially for leather color paste.

KOBOND[™] 8130 has good compatibility with various resin and it can be applied in all kinds of pigment and filler with strong dispersing ability and excellent storage stability.

PHYSICAL PROPERTIES	Color and Appearance	Yellow transparent liquid
	Ingredient	Copolymer with pigment affinity
		group
	Solvent	Solvent naphtha
	Content	50%

APPLICATIONS

• Solvent-borne leather and synthetic leather coating systems

RECOMMENDED DOSAGE

The recommended dosage as below:

Inorganic pigment	5% ~ 10%
Organic pigment	10% ~ 30%
Carbon black	20% ~ 50%

The above recommended levels can be used for orientation. Optimal levels are determined through a series of laboratory tests.

It should be added before the grinding stage during the production.

PACKING KOBOND[™] 8130 is supplied in 25Kg Pail.

HANDLING

This document does not contain the product safety information required for safe use. Before handling, please refer to the product and safety data sheets, as well as container labels, for information on safe usage, physical hazards, and health risks. Safety Data Sheet is available on the website, from the distributor, or by contacting SiSiB customer service.

SINOPCC GROUP

Product Data Sheet - Page 1/2 KOBOND™ 8130 December 2024, Version 8.1, D-R Copyright © SINOPCC GROUP www.sinopcc.com

SINOPCC GROUP

KOBOND™ 8130 Dispersant

STORAGE	When stored at temperatures between 10°C and 35°C in the original unopened containers, KOBOND [™] 8130 has a shelf life of 24 months from the date of production.
NOTE	All information in the leaflet is based on our present knowledge and experience. We reserve the right to make any changes according to technological progress or further developments. Performance of the product described herein should be verified by testing.
	We specifically disclaim any other express or implied warranty of fitness for a particular purpose or merchantability.

We disclaim liability for any incidental or consequential damages.

SINOPCC GROUP

Product Data Sheet - Page 2/2 KOBOND[™] 8130 December 2024, Version 8.1, D-R Copyright © SINOPCC GROUF www.sinopcc.com